



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
10.07.2002 Bulletin 2002/28

(51) Int Cl.⁷: **C08F 290/06, B29C 37/00,
C08G 18/67, C09D 175/16**

(21) Application number: **98300272.6**

(22) Date of filing: **15.01.1998**

(54) **In-mold coating compositions, their preparation and use**

In der Form anwendbare Beschichtungszusammensetzungen, ihre Herstellung und Verfahren
Compositions de revêtement dans le moule, leur préparation et utilisation

(84) Designated Contracting States:
BE DE FR GB IT NL SE

(30) Priority: **17.01.1997 US 785514**

(43) Date of publication of application:
22.07.1998 Bulletin 1998/30

(73) Proprietor: **OMNOVA SOLUTIONS INC.**
Fairlawn, Ohio 44333-3300 (US)

(72) Inventors:
• **McBain, Douglas S.**
Norton, Ohio 44203 (US)

- **Cobbledick, David S.**
Kent, Ohio 44240 (US)
- **Shanoski, Henry**
Akron, Ohio 44333 (US)
- **Sullivan, Brian J.**
Mogadore, Ohio 44260 (US)

(74) Representative: **Stoner, Gerard Patrick et al**
MEWBURN ELLIS
York House
23 Kingsway
London WC2B 6HP (GB)

(56) References cited:
EP-A- 0 039 588 **US-A- 4 414 173**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to in-mould coating compositions and their preparation and use, particularly but not exclusively for coating FRP (fibre-reinforced plastics) substrates.

BACKGROUND

[0002] Heretofore, in-mold coatings have been applied to fiber reinforced plastics such as sheet molded coatings to generally provide a smooth surface and reduce or eliminate substrate porosity. However, such coatings have required painting to yield desirable end use properties. Typical in-mold coatings as set forth in U.S. Patent No. 4,189,517, and U.S. Patent No. 4,222,929, to Shanoski et al., have been the reaction product of an unsaturated fumarate polyester diol, a saturated polyester diol flexibilizer, a crosslinking aliphatic polyol having from 3 to 6 hydroxyl groups, a diisocyanate, and an ethylenically unsaturated crosslinking compound such as styrene.

[0003] In-mold coating compositions, as set forth in U.S. Patent No. 4,331,735, relate to (a) a liquid crosslinkable composition having an average molecular weight of up to about 5,000, having a plurality of polymerizable ethylenic double bonds, being essentially free of active hydrogen atoms or being essentially free of isocyanate groups, (b) a material selected from the group consisting of (I) a polyisocyanate and (II) the reaction product of an excess of equivalents of a polyisocyanate and an ethylenically unsaturated compound having $-NH_2$, $-NH-$ and/or $-OH$ groups, said reaction product being free of active hydrogen atoms and (c) an organic free radical peroxide initiator in an amount sufficient to effect curing of said in-mold coating composition, said (b) being used in an amount sufficient to secure the adhesion of said coating composition to said molded thermoset resin glass fiber composition.

[0004] A large number of in-mold coatings relate to coating compositions comprising at least one polymerizable epoxy-based oligomer having at least two acrylate groups thereon, at least one copolymerizable ethylenically unsaturated monomer such as styrene, and at least copolymerizable monoethylenically unsaturated compound having a $-CO-$ group and a $-NH_2$, $-NH-$ and/or $-OH$ group, as well as a polyvinyl acetate as set forth in U.S. Patent Nos. 4,414,173, and 4,515,710 to Cobbledick et al. Still another in-mold coating relates to an epoxy-based oligomer having two acrylate end groups, and the like, as set forth in U.S. Patent No. 5,084,353 to Cobbledick.

[0005] According to the invention we provide an in-mould coating composition comprising

- (a) polyester urethane acrylate;
- (b) aliphatic or cycloaliphatic (meth)acrylate;
- (c) hydroxyalkyl (meth)acrylate;
- (d) vinyl-substituted aromatic monomer, and
- (e) polyacrylate ester of alkylene polyol.

[0006] Preferred categories, properties and proportions of these ingredients are discussed below.

[0007] Other aspects are the preparations of such a composition by blending the ingredients thereof, the use of such a composition for in-mould coating and articles/substrates e.g. of FRP, having a cured coating thereof. A particular use is as a finish coating i.e. substantially without subsequent coating.

[0008] Some particular aspects are set out in the claims. In some general aspects the cured in-mold coating compositions are made from compounds which include a saturated polyester urethane acrylate containing a saturated aliphatic polyester intermediate and a saturated aliphatic urethane group; and a saturated hydroxyl alkyl (meth)acrylate. Additionally, the use of a diacrylate ester of an alkylene diol, a saturated (cyclo)aliphatic (meth)acrylate, and a vinyl substituted aromatic have been found to impart paint coating type properties to the in-mold coating composition such as hardness, water resistance, low shrinkage, and high gloss. Optionally, in addition to the above compounds, occasionally, crosslinking agents can be utilized such as triallylcyanurate, ethoxylated trimethylolpropane triacrylate, pentaerythritol triacrylate, and the like.

[0009] The above components can be reacted, typically in the presence of a peroxide initiator to chain extend and form a thermoset resin. The cured resin can be a clear coating composition, or coloured/pigmented. The present invention thus eliminates the additional step, time and cost of applying a painted coating to the surface of a conventional in-mold coating and forms a paint-free FRP end product laminate. If a clear coating is not desired, various pigments, colorants, etc., are added to the components to yield a desired end color and opacity.

[0010] In order to achieve the in-mold coating compositions of the present invention which have paint-like properties, various compounds and resins are avoided, especially aromatic compounds such as aromatic polyesters and/or polyether urethane intermediates, aromatic epoxy-based resins, and the like.

[0011] An important aspect of the present invention, in order to achieve good paint-like properties and a clear color of the in-mold coating composition, is the utilization of a polyester intermediate urethane which contains acrylate groups, generally at the terminal portions of the polymer, and saturated aliphatic polyester moieties. A suitable urethane may

be made as follows. A polyester intermediate can be made from aliphatic dicarboxylic acids or aliphatic anhydrides and glycols and such are well known to the art and to the literature as is the preparation thereof, and are commercially available. The aliphatic dicarboxylic acids/anhydrides usually have from 1 to 15 carbon atoms and are desirable saturated (i.e., have no unsaturated carbon to carbon double bonds) with specific examples including carbonic acid, malonic acid, succinic, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, the anhydride counterparts thereof, and the like, with adipic acid generally being preferred. Mixtures of any of the above acids can be utilized as well. The glycols or diols usually have from 2 to 15 carbon atoms and are saturated with specific examples including ethylene glycol, propylene glycol, 1,3-butylene glycol, 1,4-butylene glycol, pentane diol, hexane diol, cyclohexanedimethanol dipropylene glycol, 2,2-dimethyl-1,3-propane diol, diethylene glycol, pinacol, and the like. Preferred glycols include ethylene glycol and neopentyl glycol.

[0012] The saturated aliphatic polyester intermediate usually has a number average molecular weight of from about 1,000 to about 5,000, and desirably from about 1,500 to about 2,500.

[0013] An aliphatic polyisocyanate is reacted with the saturated polyester intermediate to form a polyurethane type resin. The aliphatic portion is saturated and has from about 5 to 18 carbon atoms such as isophorone diisocyanate (IPDI), hexamethylene diisocyanate, cyclohexyl diisocyanate, and the like, with isophorone diisocyanate being preferred. The average equivalent ratio of NCO groups to OH end groups of the intermediate is approximately from about 1.5 to about 2.5, desirably from about 1.9 to about 2.1, and preferably about 2.0. Such amounts are generally sufficient to form an isocyanate terminated polyurethane prepolymer which is then reacted with a hydroxyl alkyl acrylate to form the saturated polyester urethane containing an acrylate or methacrylate, generally at the terminal portions of the polymer chain. The acrylates can generally have an ester portion containing from 2 to 10 carbon atoms, such as ethyl, propyl, n-butyl, ethylhexyl, and the like, with ethyl and propyl being preferred. An example of a preferred polyester urethane acrylate is Craynor CN 963, manufactured by Sartomer Corporation.

[0014] Polyester urethane acrylates are avoided which contain unsaturated and/or aromatic polyester intermediates, as are aromatic and/or unsaturated diisocyanates, inasmuch as they may yield a clear coating or a non-clear coating with a tendency to yellow and degrade on aging. The polyester urethane acrylates are hence substantially free of corresponding residues, i.e. they generally contain unsaturated and/or aromatic polyester residues in an amount less than 50 or 25 percent by weight, desirably less than 10 percent by weight, and preferably less than 5 percent by weight, or none at all, of such units or groups based upon the total weight of such polymer(s). Similarly, generally less than 50 or 25 percent and preferably less than 10 or 5 mole percent, or none at all, of all diisocyanate residues within the coating composition are aromatic and/or unsaturated groups based upon the total moles of isocyanate required. Other compounds or monomers preferably avoided in the formation of polyester urethane acrylates are polyethers and epoxy intermediates inasmuch as the same have been found not to yield such good

weatherability properties. Thus, the polyurethane intermediate generally contains less than 50 percent by weight and generally less than 25 percent by weight, and preferably less than 10 percent or 5 percent by weight, or none at all of polyether and/or epoxy groups based upon the total weight of the polyester urethane acrylates.

[0015] Various compounds or components are utilized to react with the polyester urethane acrylate and form a thermoset resin. One such component is an aliphatic or cycloaliphatic (meth)acrylate wherein the aliphatic and/or cycloaliphatic portion is preferably saturated, typically containing from 1 to about 50 carbon atoms and desirably from about 2 to about 20 carbon atoms. Representative examples include methyl (meth)acrylate, tetrahydrofurfuryl methacrylate, isodecylmethacrylate, 2(2-ethoxy)ethoxy ethylacrylate, stearyl acrylate, tetrahydrofurfuryl acrylate, lauryl methacrylate, stearyl methacrylate, lauryl acrylate, glycidyl methacrylate, isodecyl acrylate, isobornyl methacrylate, isooctyl acrylate, tridecyl acrylate, tridecyl methacrylate, and caprolactone acrylate, with isobornyl acrylate being preferred. The amount of the saturated (cyclo)aliphatic (meth)acrylate is generally from about 20 to about 100 parts by weight, desirably from about 35 to about 90 parts by weight, and preferably from about 50 to about 80 parts by weight per 100 total parts by weight of the polyester urethane acrylate.

[0016] Note that the aliphatic/alicyclic entity may include heteroatoms, e.g. ether oxygen and analogues thereof, but this is not a hydroxyalkyl (meth)acrylate like (c) below.

[0017] Another component utilized in the present invention is one or more hydroxy alkyl (meth)acrylates, the alkyl group usually having from 1 to 5 or 10 carbon atoms, such as methyl, ethyl, butyl, etc., with propyl being preferred. The amount of such hydroxy alkyl (meth)acrylates is usually from about 2 to about 20 parts by weight, desirably from about 6 to about 16 parts by weight, and preferably from about 8 to about 12 parts by weight per 100 parts by weight of the polyester urethane acrylate. These compounds are utilized in addition to the hydroxy alkyl methacrylates utilized to form the polyester urethane resins.

[0018] Still another component utilized in the in-mold coating compositions of the present invention are one or more vinyl substituted aromatics, typically having from 8 to 12 carbon atoms such as styrene, α -methyl-styrene, vinyl toluene, t-butyl styrene, and the like, with styrene being preferred. The amount of this component is usually from about 10 to about 70 parts by weight, desirably from about 20 to about 60 parts by weight, and preferably from about 30 to about 50 parts by weight per 100 parts by weight of the polyester urethane acrylate.

optimal
in air

[0019] Still another component is a polyacrylate such as a triacrylate or preferably a diacrylate ester of an alkylene polyol. The polyol residue preferably has from about 2 to about 30 carbon atoms, more preferably C₂₋₁₀. It is usually of a diol, such as ethylene diol, butane diol, or a triol. An acrylate which is contained on both ends of the alkylene polyol is generally derived from acrylic acid or methacrylic acid. Examples of the preferred diacrylate ester of an alkylene diol include triethylene glycol dimethacrylate, ethylene glycol dimethacrylate, tetraethylene glycol dimethacrylate, polyethylene glycol dimethacrylate, 1,3 butylene glycol diacrylate, 1,4-butanediol diacrylate, 1,4-butanediol dimethacrylate, diethylene glycol diacrylate, diethylene glycol dimethacrylate, 1,6 hexanediol diacrylate, 1,6 hexanediol dimethacrylate, neopentyl glycol diacrylate, neopentyl glycol dimethacrylate, polyethylene glycol (600) dimethacrylate, polyethylene glycol (200) diacrylate, tetraethylene glycol diacrylate, triethylene glycol diacrylate, 1,3 butylene glycol dimethacrylate, tripropylene glycol diacrylate, polyethylene glycol (400) diacrylate, polyethylene glycol (400) dimethacrylate, polyethylene glycol (600) diacrylate, propoxylated neopentyl glycol diacrylate, and alkoxylated aliphatic diacrylate. Examples of trifunctional acrylate esters of an alkylene polyol which can be optionally utilized include tris(2-hydroxy ethyl) isocyanurate trimethacrylate, trimethylolpropane trimethacrylate, trimethylolpropane triacrylate, tris(2-hydroxy ethyl) isocyanurate triacrylate, triethanolamine trimethacrylate, triethanolamine triacrylate, ethoxylated trimethylolpropane triacrylate, pentaerythritol triacrylate, propoxylated trimethylolpropane triacrylate, and propoxylated glyceryl triacrylate. The amount of the polyacrylate ester of the alkylene polyol is usually from about 10 to about 40 parts by weight, desirably from about 15 to about 35 parts by weight, and preferably from about 20 to about 30 parts by weight for every 100 parts by weight of the polyester urethane acrylate. The amount of the optional triacrylate ester of the alkylene polyol is low and usually is less than 10 parts by weight and preferably less than 5 parts by weight for every 100 parts by weight of the polyester urethane acrylate.

[0020] The above five components can combine to form the resin of the in-mold coating composition.

[0021] The initially clear coating can be colored by utilizing a pigment, a colorant, etc., in a desired or effective amount to yield a desired color, tint, hue, or opacity. Pigments and pigment dispersions are well known to the art and include, for example, titanium dioxide, carbon black, phthalocyanine blue, phthalocyanine red, chromium and ferric oxides, and the like.

[0022] The in-mold coating compositions may contain additives and fillers whose nature and quantities may be conventional. Thus, various cure inhibitors such as benzoquinone, hydroquinone, methoxyhydroquinone, p-t-butylcatechol, and the like, can be utilized. Another additive is an accelerator such as cobalt octoate. Other classes of accelerators include zinc, or other metal carboxylates. Various light stabilizers can be utilized such as, for example, the various hindered amines (HALS), substituted benzophenones, and substituted benzotriazoles, and the like. Lubricants and mold release agents are generally utilized with specific examples including various metal stearates, such as zinc stearate or calcium stearate or phosphonic acid esters. Reinforcing fillers such as talc can be utilized. Talc has also been found to help promote adhesion of the in-mold coating composition to the fiber reinforced plastic substrate. Another additive is a hardener and thixotrope such as silica. The polyester urethane acrylate and the other curing monomers or components of the present composition may be chain extended, typically by utilization of a free radical initiator such as a peroxide. Examples of suitable free radical initiators include tertiary butyl perbenzoate, tertiary butyl-peroxoate in diallyl phthalate, diacetyl peroxide in dimethyl phthalate, dibenzoyl peroxide, di(p-chlorobenzoyl) peroxide in dibutyl phthalate, di(2,4-dichlorobenzoyl) peroxide in dibutyl phthalate, dilauroyl peroxide, methyl ethyl ketone peroxide, cyclohexanone peroxide in dibutyl phthalate, 3,5-dihydroxy-3,4-dimethyl-1,2-dioxacyclopentane, t-butylperoxy(2-ethyl hexanoate), caprylyl peroxide, 2,5-dimethyl-2,5-di(benzoyl peroxy) hexane, 1-hydroxy cyclohexyl hydroperoxide-1, t-butyl peroxy (2-ethyl butyrate), 2,5-dimethyl-2,5-bis(t-butyl peroxy) hexane, cumylhydroperoxide, diacetyl peroxide, t-butyl hydroperoxide, ditertiary butyl peroxide, 3,5-dihydroxy-3,5-dimethyl-1,2-oxacyclopentane, and 1,1-bis(t-butylperoxy)-3,3,5-trimethyl cyclohexane and the like, and mixtures thereof. It is desirable sometimes to use mixtures of initiators to take advantage of their different decomposition rates and times at different temperatures and so forth. A preferred initiator to use is tertiary butyl perbenzoate. The peroxide initiator should be used in an amount sufficient to overcome the effect of the inhibitor and to cause curing of the ethylenically unsaturated compounds. Usually the peroxide initiator is used in an amount of up to about 5% or from about 0.25 to about 5%, desirably from about 1 to about 4 percent, and preferably from about 1 to about 2% by weight based on the total weight of all of the ethylenically unsaturated components employed in the in-mold coating compositions. The reaction of the polyester urethane acrylate with the curing components in the presence of the peroxide initiator is generally at a temperature of from about 200°F (93°C) to about 330°F (165°C), and desirably from about 270°F (132°C) to about 310°F (154°C).

[0023] An in-mold coating composition may conveniently be prepared as follows. The polyester urethane acrylate is mixed with the vinyl substituted aromatic monomers such as styrene, the saturated aliphatic or cycloaliphatic (meth)acrylates such as isobornyl acrylate, and the hydroxylalkyl methacrylate such as hydroxypropyl methacrylate. After these compounds are mixed, any above-noted fillers and additives such as cure inhibitors, light stabilizers, lubricants, are added and mixed. The free radical peroxide initiator is added last. The polyacrylate ester of a polyol can be present in the polyester urethane acrylate from the supplier. When an in-mold coating having a specific color is desired, one or more pigments, colorants, etc., can be utilized in suitable amounts. As known to the art, often times various pigments

or colorants are added with a carrier, for example, a polyester, so that they can be easily blended. Any conventional or suitable mixing vessel can be utilized, and the various components and additives mixed until the compounds are blended. Even if pigments are not contained in the blend, the mixture at this point is not clear. When desired, the mixed ingredients are coated onto a fiber reinforced plastic such as a sheet molded compound as by injection molding with the in-mold coating composition heated to a cure temperature. The cure temperature will vary depending upon the particular curative or peroxide utilized. Suitable cure temperatures generally range from about 200 to about 330°F (from about 93 to about 165°C). Upon cure or chain extension, the in-mold coating compound becomes clear. Traditionally, clarity can be measured by a subjective eye test, that is, the lack of any imparted color to an underlying substrate. Clarity can also be demonstrated by measuring the color of a substrate with a color spectrophotometer, both before and after coating. The data presented in Table I was obtained with a Datacolor Spectraflash® SF 600® color spectrophotometer equipped with Datamatch 600 software for paint and coatings, available from Datacolor International/Americas of Charlotte, North Carolina. The data shown in Table I shows that the brightness (L*) and color (a* and b*) are similar for both uncoated and coated substrates, where the same clear coating (Recipe A) is used in each case.

[0024] We find that in embodiments of the invention we are able to get notably good properties such as good high clarity (i.e., lack of color), good adhesion to an FRP substrate such as a sheet molded compound, good hardness, for example, a pencil hardness of at least H and desirably at least 2H, good scratch resistance, good water resistance, as well as good ultraviolet resistance. The cured thermoset in-mold coating compositions had smooth surfaces and also have high 60 degree gloss values of at least 70 and desirably at least 80. Gloss levels can also be affected by the surface and condition of the tooling used to mold parts and apply the coating. Such properties result in an in-mold coating which has a finished surface since it has good weatherability resistance and other good paint properties so that painting, which heretofore has been required, is not needed. That is, the in-mold coating composition when cured can be utilized as is with regard to a particular end use application and does not need, or is substantially free of any subsequent surface treatments, e.g., coating, another layer, etc., such as a paint, and the like. In other words, the in-mold coating composition surface is substantially treatment free meaning that generally less than 10 grams and preferably less than 5, 3, or 2 or 1 grams by weight per sq. ft. of any protective coating, film, layer, or surface treatment is applied, and preferably is totally free thereof.

[0025] The in-mold coating compositions are usually flexible and can be utilized on any surface of a fiber reinforced plastic substrate which can be a thermoplastic or a thermoset, on sheet molded compounds which are generally thermosets, on low pressure molding compounds (LPMC), and the like. Suitable end uses of the "finished" or "as is" in-mold coating compositions include various automotive parts such as spoilers, air dams, truck liners, patio furniture, satellite dishes, water craft components, and the like.

[0026] The invention will be better understood by reference to the following examples

[0027] The drawing is a chart comparing the gloss retention of embodiments of the invention with a commercial white gel coat composition.

Mixing Procedure:

Recipe A

[0028] The polyester urethane acrylate, diacrylic ester of hexane diol, styrene, isobornyl acrylate and hydroxypropyl methacrylate in the indicated amount were added to a container and mixed thoroughly using conventional mixing procedures for organic resin solutions. The hydroquinone, cobalt octoate, hindered amine light stabilizer (HALS), UV absorber, and zinc and calcium stearates were weighed into the resin solution prepared above, and again mixed thoroughly to dissolve the organics and disperse the stearates. The talc and silica were then weighed into the container with the organics and stearates, and mixed thoroughly to disperse the solids. All of the mixing occurred without external heating.

[0029] The peroxide initiator was added to the in-mold coating solution prepared above, and mixed thoroughly.

[0030] The FRP molding was prepared in a 16x16" chromed steel shear-edge mold from a conventional polyester SMC used commercially to prepare exterior automotive body panels. Molding conditions for the SMC were 300°F, (149°C) a seventy second cure time, and 1000 psi of pressure.

[0031] The coating was applied immediately following SMC cure by opening the mold, pouring in the coating on the FRP molding, and re-close of the mold. Cure conditions for the IMC were 300°F, (149°C) a sixty second cure time, and 1000 psi of pressure.

Recipe B

[0032] Same as Recipe A, with the exception of the addition and mixing of the white pigment dispersion following

EP 0 854 157 B1

the dispersion of the talc and silica, prior to the addition of the peroxide initiator.
 [0033] Preparation of in-mold coated FRP panels was the same as for Recipe A.

Recipe C

[0034] Same as Recipe A, with the exception of the addition and mixing of a phthalocyanine blue pigment dispersion.
 [0035] Preparation of in-mold coated FRP panels was the same as for Recipe A.

RECIPE A CLEAR-COAT	
	PARTS BY WT.
Polyester urethane acrylate	100.0
Diacrylic ester of hexane Diol	25.0
Styrene	42
Isobornyl acrylate	66
Hydroxypropyl methacrylate	10.1
Hydroquinone	0.23
12% Cobalt octoate in mineral oil	0.29
Hindered amine light stabilizer	1.7
UV absorber	3.4
Zinc stearate	5.5
Calcium stearate	1.8
Talc	11.4
Silica	6.8
Tertiary butyl perbenzoate	3.61

RECIPE B WHITE COLOR-COAT	
	PARTS BY WT.
Polyester urethane acrylate	100.0
Diacrylic ester of hexane diol	25.0
Styrene	42
Isobornyl acrylate	66
Hydroxypropyl methacrylate	10.1
Hydroquinone	0.23
12% Cobalt octoate in mineral oil	0.29
Hindered amine light stabilizer	1.7
UV absorber	3.4
Zinc stearate	5.5
Calcium stearate	1.8
Talc	11.4
Silica	6.8
Titanium dioxide pigment dispersion (30 wt% in unsaturated polyester)	27.4
Tertiary butyl perbenzoate	3.61

RECIPE C BLUE COLOR-COAT	
	PARTS BY WT.
Polyester urethane acrylate	100.0
Diacrylic ester of hexane diol	25.0
Styrene	42
Isobornyl acrylate	66
Hydroxypropyl methacrylate	10.1
Hydroquinone	0.23
12% Cobalt octoate in mineral oil	0.29
Hindered amine light stabilizer	1.7
UV absorber	3.4
Zinc stearate	5.5
Calcium stearate	1.8
Talc	11.4
Silica	6.8
Phthalocyanine blue pigment dispersion (25 wt% in unsaturated polyester)	13.7
Tertiary butyl perbenzoate	3.61

[0036] Recipes A, B, and C were tested with regard to various properties such as pencil hardness, tape adhesion, chip resistance and gloss as well as accelerated weathering and humidity adhesion and the results thereof are set forth in Tables 2 through 6.

TABLE 1

CIE L* a* b* Color Space D65 Illuminant, 10° Observer			
SUBSTRATE	L*	a*	b*
White uncoated	85.6	-0.86	3.03
White coated (Recipe A)	82.7	-1.12	5.56
Grey uncoated	64.9	-0.03	-0.98
Grey coated (Recipe A)	55.4	-0.39	1.02
Black uncoated	26.2	0.18	-0.76
Black coated (Recipe A)	25.7	0.17	-0.53

[0037] As noted above, very little color change occurs utilizing the clear coating of the present invention.

TABLE 2

INITIAL COATING PROPERTIES			
	RECIPE A	RECIPE B	RECIPE C
Pencil hardness	H	H	H
Tape adhesion (GM9071P)	100%	100%	100%
Cross-hatch tape adhesion (Ford BI 106-1)	0	0	0
Chip resistance (GM9506P)	8	8	8-9
60° Gloss	78	81	76

TABLE 3

COATING PROPERTIES AFTER 96 HR HUMIDITY EXPOSURE (GM4388M, GM4465P)			
	RECIPE A	RECIPE B	RECIPE C
Pencil hardness	H	H	F-H
Tape adhesion (GM9071P)	100%	100%	100%
Cross-hatch tape adhesion (Ford BI 106-1)	0	0	0
Chip resistance (GM9506P)	8	8	8
60° Gloss	72	79	73

TABLE 4

COATING PROPERTIES AFTER 10 DAY WATER IMMERSION (FORD ESB-M2P124-A1)			
	RECIPE A	RECIPE B	RECIPE C
Pencil hardness	F-H	H	HB-F
Tape adhesion (GM9071P)	100%	100%	100%
Cross-hatch tape Adhesion (Ford BI 106-1)	0	0	0
Chip resistance (GM9506P)	8	8	8-9
60° Gloss	77	68	76

TABLE 5

COATING 60° GLOSS AFTER ACCELERATED WEATHERING (SAE J1960)			
	RECIPE A	RECIPE B	RECIPE C
Initial	78	81	76
500 hours	76	86	75
1,000 hours	72	55	70
2,000 hours	58	43	50

TABLE 6

COATING PROPERTIES AFTER SIX (6) MONTH SOUTH FLORIDA EXPOSURE (5° SOUTH/BLACK BOX EXPOSURE)			
	RECIPE A	RECIPE B	RECIPE C
60° Gloss	79	77	76
Initial: Cross-hatch tape adhesion (GM9071P;A)	100%	100%	100%
Initial: Cross-hatch tape adhesion (GM9071P;B)	100%	100%	100%
After 96-hour humidity exposure: Cross-hatch tape adhesion (GM9071P;A)	100%	100%	100%
After 96-hour humidity exposure: Cross-hatch tape adhesion (GM9071P;B)	99%	97%	100%

[0038] As apparent from the tables, the in-mold coating compositions of the present invention when cured had good properties such as pencil hardness, adhesion, weatherability, and the like. The compositions of the present invention also had good gloss retention generally of at least 50%, 60%, 70%, 75%, or 80% of initial gloss, generally for at least 1,000 hours, and preferably even in an excess of 2,000 hours.

[0039] Example B of the present invention was compared with a white gel coat, which was a commercialized gel coat sold by a leading manufacturer to coat composite material watercraft.- Such gel coat materials are commercially available from many manufacturers including CCP (Cook Composites and Polymers) Kansas City, Missouri; Neste of Fort Smith, Arkansas; and Lilly Industries of Elkhart, Indiana. Gel coats are typically used in the composite industry as an appearance layer on a fiber reinforced plastic prepared by spray lay-up (or open) molding. As such, gel coats are intended for appearance and do not require paint. As apparent from the drawing, the in-mold coating composition of the present invention had very good gloss retention, even after 2,500 hours, as compared to the rapid gloss drop off at 500 hours of the control white gel coat.

Claims

1. An in-mold coating composition, comprising;

- (a) a saturated aliphatic polyester urethane acrylate, said polyester portion being derived from at least a saturated carboxylic acid or an anhydride thereof and a saturated diol, said urethane portion being derived from an aliphatic saturated polyisocyanate;
- (b) an aliphatic or cycloaliphatic (meth)acrylate wherein said aliphatic or said cycloaliphatic group is saturated and has from 1 to 50 carbon atoms;
- (c) a hydroxyalkyl (meth)acrylate wherein said alkyl group has from 1 to 10 carbon atoms,
- (d) a vinyl substituted aromatic having from 8 to 12 carbon atoms, and,
- (e) a polyacrylate ester of an alkylene polyol wherein said alkylene group has from 2 to 30 carbon atoms.

2. An in-mold coating composition according to Claim 1, wherein said (a) saturated carboxylic acid or anhydride has from 1 to 15 carbon atoms, wherein said (a) saturated diol contains from 2 to 15 carbon atoms, wherein said (a) saturated polyisocyanate includes a diisocyanate containing from 5 to 18 carbon atoms, wherein said (b) saturated aliphatic or cycloaliphatic (meth)acrylate has from 2 to 20 carbon atoms, wherein said alkyl group, of said (c) hydroxyalkyl (meth)acrylate has from 1 to 5 carbon atoms, and wherein said (e) alkylene group of said polyol has from 2 to 10 carbon atoms.

3. An in-mold coating composition according to Claim 2, wherein the amount of said (b) saturated aliphatic or cycloaliphatic (meth)acrylate is from about 20 to about 100 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate, wherein the amount of said (c) hydroxyalkyl (meth)acrylate is from about 2 parts to about 20 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate, wherein the amount of said (d) vinyl substituted aromatic is from about 10 to about 70 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate, and wherein the amount of said (e) diacrylate ester of an alkylene polyol is from 10 to 40 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate.

4. An in-mold coating composition according to Claim 3, wherein the number average molecular weight of said (a) saturated polyester portion is from about 1,000 to about 5,000, wherein said (b) saturated aliphatic or cycloaliphatic (meth)acrylate is isobornyl acrylate and wherein the amount thereof is from about 50 to about 80 parts by weight, wherein the amount of said (c) hydroxyalkyl (meth)acrylate is from about 6 to about 16 parts by weight, wherein the amount of said (d) vinyl substituted aromatic is from about 20 to about 60 parts by weight, and wherein the amount of said (e) polyacrylate ester of an alkylene polyol is from about 15 to about 35 parts by weight.

5. An in-mold coating composition according to Claim 4, wherein said (a) saturated aliphatic polyester urethane acrylate is prepared from neopentyl glycol, ethylene glycol, adipic acid, isophorone diisocyanate, and hydroxyethyl (meth)acrylate, wherein said (c) hydroxyalkyl (meth)acrylate is hydroxypropyl methacrylate, wherein said (d) vinyl substituted aromatic is styrene, and wherein said (e) polyacrylate ester of an alkylene polyol is a diacrylic ester of hexane diol.

6. An in-mold coating composition according to Claim 1, wherein said composition is reacted utilizing a peroxide initiator.

7. An in-mold coating composition according to Claim 4, wherein said composition is reacted with from about 0.25 to about 5.0 percent by weight of a peroxide initiator based upon the total weight of all of the ethylenically unsaturated components employed in the in-mold coating composition.
- 5 8. A cured, in-mold coating composition, comprising;
the reaction product of
 - (a) a saturated aliphatic polyester urethane acrylate, said polyester portion derived from at least a saturated carboxylic acid or anhydride thereof and a saturated diol, (b) an aliphatic or cycloaliphatic (meth)acrylate,
 - 10 wherein said aliphatic or said cycloaliphatic group is saturated and has from 1 to 50 carbon atoms, (c) a hydroxylalkyl (meth)acrylate, (d) vinyl substituted aromatic having a total of from 8 to 12 carbon atoms, and a (e) polyacrylate ester of an alkylene polyol wherein said alkylene group has from 2 to 12 carbon atoms in the presence of a peroxide initiator.
- 15 9. A cured, in-mold coating composition according to Claim 8, wherein the amount of said (b) saturated aliphatic or cycloaliphatic (meth)acrylate is from about 20 to about 100 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate,
 - wherein the amount of said (c) hydroxylalkyl (meth)acrylate is from about 2 parts to about 20 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate,
 - 20 wherein the amount of said (d) vinyl substituted aromatic is from about 10 to about 70 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate, and
 - wherein the amount of said (e) polyacrylate ester of an alkylene polyol is from 10 to 40 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate.
- 25 10. A cured, in-mold coating composition according to Claim 9, wherein said (a) saturated carboxylic acid or anhydride has from 1 to 15 carbon atoms, wherein said (a) saturated diol contains from 2 to 15 carbon atoms, wherein said (a) saturated polyisocyanate includes a diisocyanate containing from 5 to 18 carbon atoms,
 - wherein said (b) saturated aliphatic or cycloaliphatic (meth)acrylate has from 2 to 20 carbon atoms,
 - wherein said alkyl group of said (c) hydroxylalkyl (meth)acrylate has from 1 to 5 carbon atoms, and
 - 30 wherein said (e) alkylene group of said polyol has from 2 to 10 carbon atoms.
- 35 11. A cured, in-mold coating composition according to Claim 10, wherein the number average molecular weight of said (a) saturated polyester portion is from about 1,000 to about 5,000, wherein said saturated aliphatic polyester urethane acrylate is prepared from neopentyl glycol, ethylene glycol, adipic acid, isophorone diisocyanate, and hydroxyethyl (meth)acrylate,
 - wherein said (b) saturated aliphatic or cycloaliphatic (meth)acrylate is isobornyl acrylate and wherein the amount thereof is from about 50 to about 80 parts by weight,
 - wherein said (c) hydroxylalkyl (meth)acrylate is hydroxypropyl methacrylate and wherein the amount thereof is from about 6 to about 16 parts by weight,
 - 40 wherein said (d) vinyl substituted aromatic is styrene and wherein the amount thereof is from about 30 to about 50 parts by weight, and
 - wherein said (e) polyacrylate ester of an alkylene polyol is a diacrylic ester of hexane diol and wherein the amount thereof is from about 15 to about 35 parts by weight.
- 45 12. A cured, in-mold coating composition according to Claim 8, adhered to a fiber reinforced plastic substrate.
13. A cured, in-mold coating composition according to Claim 11, adhered to a fiber reinforced plastic substrate.
14. A cured, in-mold coating composition according to Claim 12, wherein said in-mold coating composition is substantially free of any other layer thereon.
 - 50
15. A cured, in-mold coating composition according to Claim 13, wherein said in-mold coating composition has less than 3 grams per sq. ft. of any layer thereon.
- 55 16. A cured, in-mold coating composition according to Claim 12, wherein said coating composition has a 60 degree gloss retention of at least 75% of its original value according to SAE J1960 after 1,000 hours.
17. A process for molding an in-mold coating composition onto a fiber reinforced plastic substrate and forming a coating

thereon of a predetermined thickness, comprising;

- 5 molding said substrate between separable dies which coact in a first fully-closed position to define a mold cavity corresponding in size and shape to the substrate;
 allowing said substrate to harden in said cavity;
 separating one of said dies from said substrate to provide a first gap therebetween which is greater than said predetermined thickness of said coating;
 injecting a metered amount of in-mold coating composition into said first gap, said amount being sufficient to provide said predetermined thickness but insufficient to fill said first gap;
 10 applying molding pressure to said one die to reduce said first gap to a second gap which is commensurate with said predetermined thickness and to distribute said injected material substantially uniformly throughout said second gap and over said surface;
 maintaining said pressure while said material bonds to said surface and solidifies sufficiently to permit complete separation of said dies without disruption of the coating thus formed; and
 15 completely separating said dies and removing said coated substrate from said cavity;
 the improvement comprising an in-mold composition which includes the reaction product of (a) a saturated aliphatic polyester urethane acrylate, said polyester portion derived from at least a saturated carboxylic acid or an anhydride thereof and a saturated diol, (b) an aliphatic or cycloaliphatic (meth)acrylate, (c) a hydroxylalkyl (meth)acrylate, (d) a vinyl substituted aromatic having a total of from 8 to 12 carbon atoms, and (e) a polyacrylate ester of an alkylene polyol wherein said alkylene group has from 2 to 12 carbon atoms, in the presence
 20 of a peroxide initiator so that a cured in-mold coating composition is produced.

18. A process for molding an in-mold coating composition according to Claim 17, wherein said (a) saturated carboxylic acid or anhydride has from 1 to 15 carbon atoms, wherein said (a) saturated diol contains from 2 to 15 carbon
 25 atoms, wherein said (a) saturated polyisocyanate includes a diisocyanate containing from 5 to 18 carbon atoms, wherein said (b) aliphatic or cycloaliphatic (meth)acrylate is saturated and has from 2 to 20 carbon atoms, wherein said alkyl group of said (c) hydroxylalkyl (meth)acrylate has from 1 to 5 carbon atoms, and wherein said (e) alkylene group of said polyol has from 2 to 10 carbon atoms.
- 30 19. A process for molding an in-mold coating composition according to Claim 18, wherein the amount of said (b) saturated aliphatic or cycloaliphatic (meth)acrylate is from about 20 to about 100 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate,
 wherein the amount of said (c) hydroxylalkyl (meth)acrylate is from about 2 parts to about 20 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate, and
 35 wherein the amount of said (d) vinyl substituted aromatic is from about 10 to about 70 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate, and
 wherein the amount of said (e) polyacrylate ester of an alkylene polyol is from 10 to 40 parts by weight for every 100 parts by weight of said (a) saturated aliphatic polyester urethane acrylate.
- 40 20. A process for molding an in-mold coating composition according to Claim 19, wherein said (a) saturated aliphatic polyester urethane acrylate is prepared from neopropyl glycol, ethylene glycol, adipic acid, isophorone diisocyanate, and hydroxyethyl (meth)acrylate,
 wherein said (c) hydroxylalkyl (meth)acrylate is hydroxypropyl methacrylate,
 wherein said (d) vinyl substituted aromatic is styrene, and
 45 wherein said (e) polyacrylate ester of an alkylene polyol is a diacrylic ester of hexane diol.

Patentansprüche

- 50 1. In der Form anwendbare Beschichtungszusammensetzung, umfassend:
- (a) ein gesättigtes aliphatisches Polyester-Urethanacrylat, wobei der Polyester-Anteil von zumindest einer gesättigten Carbonsäure oder einem Anhydrid davon und einem gesättigten Diol abgeleitet ist, wobei der Urethan-Anteil von einem aliphatischen gesättigten Polyisocyanat abgeleitet ist;
 55 (b) ein aliphatisches oder zykoaliphatisches (Meth)acrylat, worin die aliphatische oder die zykoaliphatische Gruppe gesättigt ist und 1 bis 50 Kohlenstoffatome aufweist;
 (c) ein Hydroxyalkyl(meth)acrylat, worin die Alkylgruppe 1 bis 10 Kohlenstoffatome aufweist,
 (d) einen Vinyl-substituierten Aromaten, der 8 bis 12 Kohlenstoffatome aufweist, und

(e) einen Polyacrylatester eines Alkylpolyols, worin die Alkylengruppe 2 bis 30 Kohlenstoffatome aufweist.

2. In der Form anwendbare Beschichtungszusammensetzung nach Anspruch 1, worin die unter (a) erwähnte gesättigte Carbonsäure oder deren Anhydrid 1 bis 15 Kohlenstoffatome aufweist, worin das unter (a) erwähnte gesättigte Diol 2 bis 15 Kohlenstoffatome enthält, worin das unter (a) erwähnte gesättigte Polyisocyanat ein Diisocyanat umfasst, das 5 bis 18 Kohlenstoffatome enthält,
 worin das unter (b) erwähnte, gesättigte, aliphatische oder zykloliphatische (Meth)acrylat 2 bis 20 Kohlenstoffatome aufweist,
 worin die Alkylgruppe des unter (c) erwähnten Hydroxyalkyl(meth)acrylats 1 bis 5 Kohlenstoffatome aufweist,
 und
 worin die Alkylengruppe des unter (e) erwähnten Polyols 2 bis 10 Kohlenstoffatome aufweist.

3. In der Form anwendbare Beschichtungszusammensetzung nach Anspruch 2, worin die Menge des unter (a) erwähnten, gesättigten, aliphatischen oder zykloliphatischen (Meth)acrylats etwa 20 bis etwa 100 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt,
 worin die Menge des unter (c) erwähnten Hydroxyalkyl(meth)acrylats etwa 2 bis etwa 20 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt,
 worin die Menge des unter (d) erwähnten Vinyl-substituierten Aromaten etwa 10 bis 70 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt, und
 worin die Menge des unter (e) erwähnten Diacrylatesters eines Alkylpolyols 10 bis 40 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt.

4. In der Form anwendbare Beschichtungszusammensetzung nach Anspruch 3, worin das zahlenmittlere Molekulargewicht des unter (a) erwähnten gesättigten Polyester-Anteils etwa 1.000 bis etwa 5.000 beträgt,
 worin das unter (b) erwähnte, gesättigte, aliphatische oder zykloliphatische (Meth)acrylat Isobornylacrylat ist und worin dessen Menge etwa 50 bis etwa 80 Gewichtsteile beträgt,
 worin die Menge des unter (c) erwähnten Hydroxyalkyl(meth)acrylats etwa 6 bis etwa 16 Gewichtsteile beträgt,
 worin die Menge des unter (d) erwähnten Vinyl-substituierten Aromaten etwa 20 bis etwa 60 Gewichtsteile beträgt, und
 worin die Menge des unter (e) erwähnten Polyacrylatesters eines Alkylpolyols etwa 15 bis etwa 35 Gewichtsteile beträgt.

5. In der Form anwendbare Beschichtungszusammensetzung nach Anspruch 4, worin das unter (a) erwähnte, gesättigte, aliphatische Polyester-Urethanacrylat aus Neopentylglykol, Ethylenglykol, Adipinsäure, Isophorondiisocyanat und Hydroxyethyl(meth)-acrylat hergestellt ist,
 worin das unter (c) erwähnte Hydroxyalkyl(meth)acrylat Hydroxypropylmethacrylat ist,
 worin der unter (d) erwähnte Vinyl-substituierte Aromat Styrol ist, und
 worin der unter (e) erwähnte Polyacrylatester eines Alkylpolyols ein Hexandioldiacrylsäureester ist.

6. In der Form anwendbare Beschichtungszusammensetzung nach Anspruch 1, worin die Zusammensetzung unter Verwendung eines Peroxidinitiators umgesetzt wird.

7. In der Form anwendbare Beschichtungszusammensetzung nach Anspruch 4, worin die Zusammensetzung mit etwa 0,25 bis etwa 5,0 Gewichtsteilen eines Peroxidinitiators, bezogen auf das Gesamtgewicht aller in der in der Form anwendbaren Beschichtungszusammensetzung eingesetzten ethylenisch ungesättigten Komponenten umgesetzt wird.

8. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung, umfassend:

das Reaktionsprodukt von

(a) einem gesättigten aliphatischen Polyester-Urethanacrylat, wobei der Polyester-Anteil von zumindest einer gesättigten Carbonsäure oder einem Anhydrid davon und einem gesättigten Diol abgeleitet ist, (b) einem aliphatischen oder zykloliphatischen (Meth)acrylat, worin die aliphatische oder die zykloliphatische Gruppe gesättigt ist und 1 bis 50 Kohlenstoffatome aufweist, (c) einem Hydroxyalkyl(meth)acrylat, (d) Vinylsubstituiertem Aromaten mit insgesamt 8 bis 12 Kohlenstoffatomen, und (e) einem Polyacrylatester eines Alkylpolyols, worin die Alkylengruppe 2 bis 12 Kohlenstoffatome aufweist, in Gegenwart eines

Peroxidinitiators.

- 5 9. Gehärtete; in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 8, worin die Menge des unter (b) erwähnten, gesättigten, aliphatischen oder zykoaliphatischen (Meth)acrylats etwa 20 bis etwa 100 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt,
 worin die Menge des unter (c) erwähnten Hydroxyalkyl(meth)acrylats etwa 2 bis etwa 20 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt,
 worin die Menge des unter (d) erwähnten Vinyl-substituierten Aromaten etwa 10 bis etwa 70 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt, und
 worin die Menge des unter (e) erwähnten Polyacrylatesters eines Alkylenpolyols 10 bis 40 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt.
- 10 10. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 9, worin die unter (a) erwähnte gesättigte Carbonsäure oder deren Anhydrid 1 bis 15 Kohlenstoffatome aufweist, worin das unter (a) erwähnte gesättigte Diol 2 bis 15 Kohlenstoffatome enthält, worin das unter (a) erwähnte gesättigte Polyisocyanat ein Diisocyanat umfasst, das 5 bis 18 Kohlenstoffatome enthält,
 worin das unter (b) erwähnte, gesättigte, aliphatische oder zykoaliphatische (Meth)acrylat 2 bis 20 Kohlenstoffatome aufweist,
 20 worin die Alkylgruppe des unter (c) erwähnten Hydroxyalkyl(meth)acrylats 1 bis 5 Kohlenstoffatome aufweist, und
 worin die Alkylengruppe des unter (e) erwähnten Polyols 2 bis 10 Kohlenstoffatome aufweist.
- 25 11. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 10, worin das zahlenmittlere Molekulargewicht des unter (a) erwähnten gesättigten Polyester-Anteils etwa 1.000 bis etwa 5.000 beträgt, worin das gesättigte aliphatische Polyester-Urethanacrylat aus Neopentylglykol, Ethylenglykol, Adipinsäure, Isophoron-diisocyanat und Hydroxyethyl(meth)acrylat hergestellt ist,
 worin das unter (b) erwähnte, gesättigte, aliphatische oder zykoaliphatische (Meth)acrylat Isobornylacrylat ist und worin dessen Menge etwa 50 bis etwa 80 Gewichtsteile beträgt,
 30 worin das unter (c) erwähnte Hydroxyalkyl(meth)acrylat Hydroxypropylmethacrylat ist und worin dessen Menge etwa 6 bis etwa 16 Gewichtsteile beträgt,
 worin der unter (d) erwähnte Vinyl-substituierte Aromat Styrol ist und worin dessen Menge etwa 30 bis etwa 50 Gewichtsteile beträgt, und
 worin der unter (e) erwähnte Polyacrylatester eines Alkylenpolyols ein Hexandioldiacrylsäureester ist und
 35 worin dessen Menge etwa 15 bis etwa 35 Gewichtsteile beträgt.
12. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 8, die an einem faserverstärkten Kunststoffsubstrat haftet.
- 40 13. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 11, die an einem faserverstärkten Kunststoffsubstrat haftet.
14. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 12, worin die in der Form anwendbare Beschichtungszusammensetzung im Wesentlichen frei von einer anderen Schicht darauf ist.
- 45 15. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 13, worin die in der Form anwendbare Beschichtungszusammensetzung weniger als 3 g pro Quadratfuß irgendeiner Schicht darauf aufweist.
- 50 16. Gehärtete, in der Form anwendbare Beschichtungszusammensetzung nach Anspruch 12, worin die Beschichtungszusammensetzung gemäß SAE J1960 nach 1.000 h eine 60-Grad-Glanzbeständigkeit von zumindest 75 % ihrer Ausgangswerts aufweist.
- 55 17. Verfahren zum Formen einer in der Form anwendbaren Beschichtungszusammensetzung auf ein faserverstärktes Kunststoffsubstrat und Ausbilden eines Überzugs mit einer vorbestimmten Dicke darauf, umfassend:

das Formen des Substrats zwischen trennbaren Formen, die in einer ersten, vollständig geschlossenen Position gemeinsam einen Formhohlraum definieren, der in Größe und Gestalt dem Substrat entspricht;

das Härtenlassen des Substrats im Hohlraum;
 das Trennen einer der Formen vom Substrat, um einen ersten Zwischenraum dazwischen bereitzustellen, der größer als die vorbestimmte Dicke des Überzugs ist;
 das Einspritzen einer dosierten Menge an in der Form anwendbarer Beschichtungszusammensetzung in den ersten Zwischenraum, wobei die Menge ausreicht, um für die vorbestimmte Dicke zu sorgen, aber nicht ausreicht, um den ersten Zwischenraum zu füllen;
 das Ausüben von Formdruck auf die eine Form, um den ersten Zwischenraum auf einen zweiten Zwischenraum zu verringern, der der vorbestimmten Dicke entspricht, und um das eingespritzte Material im Wesentlichen gleichmäßig im gesamten zweiten Zwischenraum und auf der Oberfläche zu verteilen;
 das Beibehalten des Drucks, während sich das Material an die Oberfläche bindet und ausreichend verfestigt, vom vollständigen Trennen der Formen ohne Unterbrechung des so gebildeten Überzugs zu ermöglichen; und
 das vollständige Trennen der Formen und das Entfernen des beschichteten Substrats aus dem Hohlraum;

wobei die Verbesserung eine in der Form anwendbare Zusammensetzung umfasst, die das Reaktionsprodukt von (a) einem gesättigten aliphatischen Polyester-Urethanacrylat, wobei der Polyester-Anteil von zumindest einer gesättigten Carbonsäure oder einem Säureanhydrid davon und einem gesättigten Diol abgeleitet ist, (b) einem aliphatischen oder zykoaliphatischen (Meth)acrylat, (c) einem Hydroxyalkyl(meth)acrylat, (d) einem Vinyl-substituierten Aromaten mit insgesamt 8 bis 12 Kohlenstoffatomen, und (e) einem Polyacrylatester eines Alkylenpolyols, worin die Alkylengruppe 2 bis 12 Kohlenstoffatome aufweist, in Gegenwart eines Peroxid-Initiators umfasst, so dass eine gehärtete, in der Form anwendbare Beschichtungszusammensetzung erzeugt wird.

18. Verfahren zum Formen einer in der Form anwendbaren Beschichtungszusammensetzung nach Anspruch 17, worin die unter (a) erwähnte gesättigte Carbonsäure oder deren Anhydrid 1 bis 15 Kohlenstoffatome aufweist, worin das unter (a) erwähnte gesättigte Diol 2 bis 15 Kohlenstoffatome enthält, worin das unter (a) erwähnte gesättigte Polyisocyanat ein Diisocyanat umfasst, das 5 bis 18 Kohlenstoffatome enthält,
 worin das unter (b) erwähnte aliphatische oder zykoaliphatische (Meth)acrylat gesättigt ist und 2 bis 20 Kohlenstoffatome aufweist,
 worin die unter (c) erwähnte Alkylgruppe des Hydroxyalkyl(meth)acrylats 1 bis 5 Kohlenstoffatome aufweist und
 worin die Alkylengruppe des unter (e) erwähnten Polyols 2 bis 10 Kohlenstoffatome aufweist.

19. Verfahren zum Formen einer in der Form anwendbaren Beschichtungszusammensetzung nach Anspruch 18, worin die Menge des unter (b) erwähnten, gesättigten, aliphatischen oder zykoaliphatischen (Meth)acrylats etwa 20 bis etwa 100 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt,
 worin die Menge des unter (c) erwähnten Hydroxyalkyl(meth)acrylats etwa 2 bis etwa 20 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt, und
 worin die Menge des unter (d) erwähnten Vinyl-substituierten Aromaten etwa 10 bis etwa 70 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt, und
 worin die Menge des unter (e) erwähnten Polyacrylatesters eines Alkylenpolyols 10 bis 40 Gewichtsteile pro 100 Gewichtsteile des unter (a) erwähnten, gesättigten, aliphatischen Polyester-Urethanacrylats beträgt.

20. Verfahren zum Formen einer in der Form anwendbaren Beschichtungszusammensetzung nach Anspruch 19, worin das unter (a) erwähnte, gesättigte, aliphatische Polyester-Urethanacrylat aus Neopropylglykol, Ethylenglykol, Adipinsäure, Isophorondiisocyanat und Hydroxyethyl(meth)acrylat hergestellt ist,
 worin das unter (c) erwähnte Hydroxyalkyl(meth)acrylat Hydroxypropylmethacrylat ist,
 worin der unter (d) erwähnte Vinyl-substituierte Aromat Styrol ist und
 worin der unter (e) erwähnte Polyacrylatester eines Alkylenpolyols ein Hexandioldiacrylsäureester ist.

Revendications

1. Composition de revêtement dans le moule, comprenant:

(a) un polyester aliphatique saturé acrylate d'uréthane, ladite portion de polyester étant dérivée d'au moins un acide carboxylique saturé ou son anhydride et d'un diol saturé, ladite portion d'uréthane étant dérivée d'un polyisocyanate aliphatique saturé;
 (b) un (méth)acrylate aliphatique ou cycloaliphatique où ledit groupe aliphatique ou cycloaliphatique est saturé

et a de 1 à 50 atomes de carbone;

(c) un hydroxyalkyl (méth)acrylate où ledit groupe alkyle a de 1 à 10 atomes de carbone,

(d) un aromatique vinyle substitué ayant de 8 à 12 atomes de carbone, et,

(e) un ester de polyacrylate d'un alkylène polyol où ledit groupe alkylène a de 2 à 30 atomes de carbone.

5

2. Composition de revêtement dans le moule selon la revendication 1, où ledit (a) acide carboxylique saturé ou anhydride a de 1 à 15 atomes de carbone, où ledit (a) diol saturé contient de 2 à 15 atomes de carbone, où ledit (a) polyisocyanate saturé contient un diisocyanate contenant de 5 à 18 atomes de carbone,

où ledit (b) (méth)acrylate aliphatique ou cycloaliphatique saturé a de 2 à 20 atomes de carbone,

10

où ledit groupe alkyle dudit (c) hydroxyalkyl (méth)acrylate a de 1 à 5 atomes de carbone, et

où ledit (e) groupe alkylène dudit polyol a de 2 à 10 atomes de carbone.

3. Composition de revêtement dans le moule selon la revendication 2, où la quantité dudit (b) (méth)acrylate aliphatique ou cycloaliphatique saturé est d'environ 20 à environ 100 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane,

15

où la quantité dudit (c) hydroxy alkyl (méth)acrylate est d'environ 2 parties à environ 20 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane,

où la quantité dudit (d) aromatique vinyle substitué est d'environ 10 à environ 70 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane, et

20

où la quantité dudit (e) diacrylate ester d'un alkylène polyol est de 10 à 40 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane.

4. Composition de revêtement dans le moule selon la revendication 3, où le poids moléculaire moyen en nombre de ladite (a) portion de polyester saturé est d'environ 1 000 à environ 5 000,

25

où ledit (b) (méth)acrylate aliphatique ou cycloaliphatique saturé est l'acrylate d'isobornyle et où sa quantité est d'environ 50 à environ 80 parties en poids,

où la quantité dudit (c) hydroxyalkyl (méth)acrylate est d'environ 6 à environ 16 parties en poids,

où la quantité dudit (d) aromatique vinyle substitué est d'environ 20 à environ 60 parties en poids, et

où la quantité dudit (e) ester de polyacrylate d'un alkylène polyol est d'environ 15 à environ 35 parties en poids.

30

5. Composition de revêtement dans le moule selon la revendication 4, où ledit (a) polyester aliphatique saturé acrylate d'uréthane est préparé à partir de néopentyl glycol, éthylène glycol, acide adipique, diisocyanate d'isophorone et hydroxyéthyl (méth)acrylate,

35

où ledit (c) hydroxyalkyl (méth)acrylate est hydroxypropyl méthacrylate,

où ledit (d) aromatique vinyle substitué est du styrène, et

où ledit (e) ester de polyacrylate d'un alkylène polyol est un ester diacrylique d'hexane diol.

6. Composition de revêtement dans le moule selon la revendication 1, où ladite composition est mise à réagir en utilisant un initiateur de peroxyde.

40

7. Composition de revêtement dans le moule selon la revendication 4, où ladite composition est mise à réagir avec environ 0,25 à environ 5,0 pour cent en poids d'un initiateur de peroxyde, en se basant sur le poids total de tous les composants à insaturation éthylénique employés dans la composition de revêtement dans le moule.

45

8. Composition de revêtement dans le moule, durcie, comprenant:

le produit de réaction de

50

(a) un polyester aliphatique saturé acrylate d'uréthane, ladite portion de polyester dérivée d'au moins un acide carboxylique saturé ou son anhydride et un diol saturé, (b) un (méth)acrylate aliphatique ou cycloaliphatique où ledit groupe aliphatique ou cycloaliphatique est saturé et a de 1 à 50 atomes de carbone, (c) un hydroxyalkyl (méth)acrylate, (d) un aromatique vinyle substitué ayant un total de 8 à 12 atomes de carbone, et un (e) ester de polyacrylate d'un alkylène polyol où ledit groupe alkylène a de 2 à 12 atomes de carbone en présence d'un initiateur de peroxyde.

55

9. Composition de revêtement dans le moule, durcie, selon la revendication 8, où la quantité dudit (b) (méth)acrylate aliphatique ou cycloaliphatique saturé est d'environ 20 à environ 100 parties en poids pour 100 parties en poids

- dudit (a) polyester aliphatique saturé acrylate d'uréthane,
 où la quantité dudit (c) hydroxyalkyl (méth)acrylate est d'environ 2 parties à environ 20 parties en poids pour
 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane,
 où la quantité dudit (d) aromatique vinyle substitué est d'environ 10 à environ 70 parties en poids pour 100
 5 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane, et
 où la quantité dudit (e) ester de polyacrylate d'un alkylène polyol est de 10 à 40 parties en poids pour 100
 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane.
10. Composition de revêtement dans le moule, durcie, selon la revendication 9, où ledit (a) acide carboxylique saturé
 10 ou anhydride a de 1 à 15 atomes de carbone, où ledit (a) diol saturé contient de 2 à 15 atomes de carbone, où
 ledit (a) polyisocyanate saturé comporte un diisocyanate contenant de 5 à 18 atomes de carbone,
 où ledit (b) (méth)acrylate aliphatique ou cycloaliphatique saturé a de 2 à 20 atomes de carbone,
 où ledit groupe alkyle dudit (c) hydroxyalkyl (méth)acrylate a de 1 à 5 atomes de carbone, et
 où ledit (e) groupe alkylène dudit polyol a de 2 à 10 atomes de carbone.
- 15 11. Composition de revêtement dans le moule, durcie, selon la revendication 10, où le poids moléculaire moyen en
 nombre de ladite (a) portion de polyester saturé est d'environ 1.000 à environ 5.000, où ledit polyester aliphatique
 saturé acrylate d'uréthane est préparé à partir de néopentyl glycol, éthylène glycol, acide adipique, diisocyanate
 d'isophorone et hydroxyéthyl (méth)acrylate,
 20 où ledit (b) (méth)acrylate aliphatique ou cycloaliphatique saturé est l'acrylate d'isobornyle et où sa quantité
 est d'environ 50 à environ 80 parties en poids,
 où ledit (c) hydroxyalkyl (méth)acrylate est l'hydroxypropyl méthacrylate et où sa quantité est d'environ 6 à
 environ 16 parties en poids,
 où ledit (d) aromatique vinyle substitué est du styrène et où sa quantité est d'environ 30 à environ 50 parties
 25 en poids, et
 où ledit (e) ester de polyacrylate d'un alkylène polyol est un ester diacrylique d'hexane diol et où sa quantité
 est d'environ 15 à environ 35 parties en poids.
12. Composition de revêtement dans le moule, durcie, selon la revendication 8, qui adhère à un substrat en plastique
 30 renforcé de fibres.
13. Composition de revêtement dans le moule, durcie, selon la revendication 11, qui adhère à un substrat en plastique
 renforcé de fibres.
- 35 14. Composition de revêtement dans le moule, durcie, selon la revendication 12, où ladite composition de revêtement
 dans le moule est sensiblement exempte de toute autre couche par-dessus.
15. Composition de revêtement dans le moule, durcie, selon la revendication 13, où ladite composition de revêtement
 dans le moule a moins de 3 grammes par pied carré de toute couche par-dessus.
- 40 16. Composition de revêtement dans le moule, durcie, selon la revendication 12, où ladite composition de revêtement
 a une conservation du brillant à 60 degrés d'au moins 75% de sa valeur d'origine selon SAE J1960 au bout de
 1.000 heures.
- 45 17. Procédé pour le moulage d'une composition de revêtement dans le moule sur un substrat en plastique renforcé
 de fibres et la formation d'un revêtement par-dessus d'une épaisseur prédéterminée, comprenant:
- le moulage dudit substrat entre des matrices séparables qui coopèrent dans une première position totalement
 fermée pour définir une cavité de moule correspondant en dimension et en forme au substrat;
 50 le durcissement dudit substrat dans ladite cavité;
 la séparation de l'une desdites matrices dudit substrat pour former un premier espace entre eux qui est plus
 grand que ladite épaisseur prédéterminée dudit revêtement;
 l'injection d'une quantité dosée de la composition de revêtement dans le moule dans ledit premier espace,
 ladite quantité étant suffisante pour produire ladite épaisseur prédéterminée mais insuffisante pour remplir
 55 ledit premier espace;
 l'application d'une pression de moulage à ladite première matrice pour réduire ledit premier espace à un second
 espace qui est en mesure avec ladite épaisseur prédéterminée et pour distribuer ladite matière injectée sen-
 siblement uniformément à travers tout ledit second espace et sur ladite surface;

le maintien de ladite pression alors que ladite matière se colle à ladite surface et se solidifie suffisamment pour permettre une séparation complète desdites matrices sans rupture du revêtement ainsi formé; et la séparation complète desdites matrices et l'enlèvement dudit substrat revêtu de ladite cavité;

l'amélioration comprenant une composition dans le moule qui comprend le produit réactionnel de (a) un polyester aliphatique saturé acrylate d'uréthane, ladite portion de polyester dérivée d'au moins un acide carboxylique saturé ou son anhydride et un diol saturé, (b) un (méth)acrylate aliphatique ou cycloaliphatique, (c) un hydroxyalkyl (méth)acrylate, (d) un aromatique vinyle substitué ayant un total de 8 à 12 atomes de carbone, et (e) un ester de polyacrylate d'un alkylène polyol où ledit groupe alkylène a de 2 à 12 atomes de carbone, en présence d'un initiateur de peroxyde de façon qu'une composition de revêtement dans le moule durcie soit produite.

18. Procédé pour le moulage d'une composition de revêtement dans le moule selon la revendication 17, où ledit (a) acide carboxylique saturé ou anhydride a de 1 à 15 atomes de carbone, où ledit (a) diol saturé contient de 2 à 15 atomes de carbone, où ledit (a) polyisocyanate saturé comporte un diisocyanate contenant de 5 à 18 atomes de carbone,

où ledit (b) (méth)acrylate aliphatique ou cycloaliphatique est saturé et a de 2 à 20 atomes de carbone, où ledit groupe alkyle dudit (c) hydroxyalkyl (méth)acrylate a de 1 à 5 atomes de carbone, et où ledit (e) groupe alkylène dudit polyol a de 2 à 10 atomes de carbone.

19. Procédé pour le moulage d'une composition de revêtement dans le moule selon la revendication 18, où la quantité dudit (b) (méth)acrylate aliphatique ou cycloaliphatique saturé est d'environ 20 à environ 100 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane,

où la quantité dudit (c) hydroxyalkyl (méth)acrylate est d'environ 2 parties à environ 20 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane, et

où la quantité dudit (d) aromatique vinyle substitué est d'environ 10 à environ 70 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane, et

où la quantité dudit (e) ester de polyacrylate d'un alkylène polyol est de 10 à 40 parties en poids pour 100 parties en poids dudit (a) polyester aliphatique saturé acrylate d'uréthane.

20. Procédé pour le moulage d'une composition de revêtement dans le moule selon la revendication 19, où ledit (a) polyester aliphatique saturé acrylate d'uréthane est préparé à partir de néopropyl glycol, éthylène glycol, acide adipique, diisocyanate d'isophorone et hydroxyéthyl (méth)acrylate,

où ledit (c) hydroxyalkyl (méth)acrylate est hydroxypropyl méthacrylate,

où ledit (d) aromatique vinyle substitué est du styrène, et

où ledit (e) ester de polyacrylate d'un alkylène polyol est un ester diacrylique d'hexane diol.

